

MECODUR[®] H 5580 LMC

Hardener for dispersion-based flocking adhesives

MECODUR H 5580 LMC is a hardener (curing agent) for a number of dispersion-based flocking adhesives. As the curing-conditions and adding quantities vary, these data are to be taken from the resp. Technical Information Sheets of the adhesives used.

Base	Poly-Isocyanate
Colour	Colourless to yellowish, translucent to slightly cloudy
Solid contents	100 %
NCO contents	23 % approx. (according to DIN 53185)
Density	1,2 g/cm ³ approx.
Flash Point	+ 170° C approx.
Safety tips/ Environmental protection	Please check the resp. safety data sheet of those products used.
Storage	1 year (at 5° to 30° C in the original packing). Opened containers have to be closed tightly again.

This data sheet is for your information. A legally binding assurance of the product's suitability for a specific purpose cannot be derived from it and no liability can be assumed for any potential damages that may occur. Liability for damages due to a slightly negligent breach of duty on our part or on the part of our legal representative or vicarious agent is excluded. Our liability for damages due to injury to life, body or health is not covered by this limitation of liability. Our products are subject to continuous production and quality control and leave our company in perfect condition.

This product is intended solely for industrial applications and not for use by the end consumer. We recommend to our customers to always test the product themselves since only in this way – also after production – can the freedom from certain substances and the suitability for a particular purpose be verified. The user has to test the product for suitability for the intended application. We reserve the right to modify product specifications. Tests that are not part of the specifications of the product mentioned above have not been carried out. All information applies only to the above-mentioned product obtained from Kissel + Wolf GmbH. It corresponds to our current state of knowledge, but is not a confirmation of a particular application and is not automatically replenished.

All information is valid for a maximum of 12 months from the date stated above (annexes may be provided with their own date). Any industrial property rights as well as existing laws and regulations are to be observed by the recipient of our product on his own responsibility. Intellectual property rights of third parties must be observed. Our terms and conditions of sale and delivery shall apply.